

# FIX-REVOCO

**Pre-mixed cement for RENDERS on walls. It is a CONSISTENT QUALITY mortar, for when a safe, durable and fast application is needed.**

## Appropriate substrates for using FIX-REVOCO:

- ◆ FIX-REVOCO can be applied as render on walls made of brick, concrete, mortar, cement slabs...
- ◆ These substrates must be clean, sturdy, solid, not disintegrating, etc.
- ◆ Ambient temperature should be between +5°C and +35°C.

## Preparing the substrate:

### Firstly, choose one of the two cases:

- ◆ Are you applying render in an interior location?
  - check on the substrate's absorption. How is that done?
  - using a brush, dampen the substrate with water.
  - touch the substrate with your hand: if your hand is wet, make sure you do NOT dampen the substrate before applying the render.
  - however, if your hand is NOT wet when you touch the substrate, then you MUST dampen the substrate before applying the render.
- ◆ Are you applying render in a swimming pool?
  - If you have concerns about substrate absorption in these cases, then it is doubtlessly better to apply a first coat of adhesive grout beforehand, mixing 1 part PRIMFIX liquid adhesive with 1 part Portland cement.



## ATTENTION

- ◆ FIX-REVOCO must be mixed only with water. Do NOT add sand.
- ◆ Do not use FIX-REVOCO for purposes other than those indicated.
- ◆ FIX-REVOCO is not a mortar for laying tile.



Adhesive grout: PRIMFIX + pure Portland cement.



A "plastic" consistency mortar.

## Preparing FIX-REVOCO mortar:

- ◆ Mix with 2.5 litres of water for every 25 kg of Fix-REVOCO.
- ◆ Mix in a cement-mixer or with a mixer.
- ◆ Mix it until the mortar has a plastic consistency and is pleasant to the touch. If necessary, add a bit more water, but not too much.



**1ST STEP: VERY IMPORTANT**

- ◆ Apply a **first coat** of **FIX-REVOCO** with the thin part of the plastering trowel.



Firstly, apply a thin coat.

**2ND STEP: Spread the mortar**

- ◆ Once the thin coat mentioned above has been extended, all that's left is to fill in the space between the two screeds, and level it...



Firstly, apply a thin coat.

**3RD STEP: Levelling**

- ◆ As if it were ordinary mortar, level the surface the usual way.



Use the usual tools.



Use the usual tools.

**4th STEP (optional): Smoothing**

- ◆ If the thinnest possible layer of **FIX-REVOCO** is desired, it can be easily smoothed using a thin plastering trowel.



If necessary, it can also be smoothed.

COVERAGE:	
Adhesive grout (when needed)	Portland: 0.2 kg/m <sup>2</sup> PRIMFIX: 0.2 l/m <sup>2</sup>
<b>FIX-REVOCO</b>	15-18 kg/m <sup>2</sup> per cm. of thickness (always depending on the level of compactness)



Consistent quality renders.

